

ZETAFIL CST 1

RAW MATERIALS

ΠΡΩΤΕΣ ΥΛΕΣ

Zetafil CST 1 is based on a very white and pure crystalline $CaCO_3$ raw material. Zetafil CST 1 is specially coated by an organic agent which transforms the surface of the inorganic particles into an organic one, thus achieving full compatibility of the filler to the resin. Due to its special particle size distribution and hydrophobic surface, Zetafil CST 1 is easily dispersed. Zetafil CST 1's brightness value enables formulators to economize in Titanium Dioxide. The abrasive index of Zetafil cst 1 is exceptionally low due to the purity of the raw material, the fineness of its particles and the coating of its surface.

CHEMICAL ANALYSIS		XHI	ΜΙΚΗ ΑΝΑΛΥΣΗ
CaCO ₃	: 99.500%	Fe ₂ O ₃	: 0.010%
MgO	: 0.320 %	Al ₂ O ₃	: 0.003%
SiO ₂	: 0.040%	Loss on ignition Moisture (DIN 53198) below 0.	: 44.97% 2%

FINENESS

		Particle Size Distribution Curve		
d (0.97) d (0.50) Finer than 2 microns Measured by Malvern - 2	: 3.5 microns. : 1.1 microns. : 70 % 000 instruments.	100 90 80 70 60 50 40 30 20 10 0 2 2 4 6 7 7 40 10 0 0 2 4 6 7 7 6 7 7 8 7 7 7 8 7 7 8 7 7 8 7 7 8 7 8		

TECHNICAL DATA		ΤΕΧΝΙΚΗ ΕΝΔΕΙΞΗ
Density (ISO 787/10)	: 2.7 gr/cm ³ .	
Refractive index	: 1.59.	
Hardness (Mohs)	: 3.	
Particle shape	: Micro - crystalline rhombohedral.	
Packed bulk density	: 0.90 gr/cm ³ .	
Dry brightness (DIN 6174)	: 98%	
pH value (ISO 787/9)	: 9.	THESE FIGURES ARE AVERAGE VALUES FROM NUMEROUS
Oil absorption (ISO 787/5)	: 19 gr per 100 gr powder.	MEASUREMENTS. THEY CANNOT, HOWEVER, BE TAKEN AS BINDING.
D.O.P. absorption (ISO 787/5)	: 21 gr per 100 gr powder.	HOWEVEN, DE TAKEN AS BINDING.

APPLICA	FIONS			ΕΦΑΡΜΟΓΗ
Plastics:	Rigid PVC Window profiles	Polyolefins Colour Masterbatch	Paints:	High gloss enamels
	Calendered Sheets Profiles\pipes Mouldings	Compound \ masterbatch for mouldings	Elastomers:	

λεπτοτής